

# LODGE TECHNICAL SPECIFICATIONS

Lodge is pure aniline, cracked grain leather with a shine, cracked pull-up finish. As a Leathershield product, it offers excellent durability for medium traffic areas with minimal maintenance.



PROPERTY	TEST METHOD	RESULT
Average Hide Size		50 FT2
Average Thickness	ISO 2589	0.9 - 1.1 mm
Tensile Strength	ISO 3376	na
Elongation at Break	ISO 3376	Traction > 11N/mmsq.
Tear Strength	ISO 3377-2	> 40/Nmm
Flexing Endurance	ISO 5402	No Visible Cracking
Color Fastness to Artificial Light (Xenotest 72 Hrs.)	ISO 105 B 02	3/4 (Grey Scale)
Color Fastness to Rubbing (50 Dry Rubs, 20 Wet Rubs)	ISO 11640 , ISO 11640	50 Cycles, 20 Cycles
California Technical	Cal Tech Bulletin 117-2013	Class 1
Cigarette Ignition Resistance	UFAC/NFPA 260	Class 1
Wyzenbeek - (Oscillatory Cylinder Method) @ 100,000 cycles	ASTM D 4157.13	Pass
Water Repellency Spray Test	AATCC #22-2017	70
Soil Release: Oily Stain Release Method	AATC #130-2018	Veg Oil (Grade 5), Ketchup (Grade 5), Red Wine (Grade 5)