

VERONA TECHNICAL SPECIFICATIONS

Verona is semi-aniline, enhanced grain leather with a matte finish. As a Leathershield product, it offers excellent durability for heavy traffic areas with minimal maintenance.



PROPERTY	TEST METHOD	RESULT
Average Thickness	ASTM D 1813	1.21MM
Breaking Strength	ASTM D2208	777,38N
Elongation at 400N	ASTM D2209	56,76%
Tear Strength	ASTM D5733	87,55
Seam Fatigue Resistance	FLTM BN 106-02	3,00MM
Stiffness	IUP 36	4,20MM
Resistance to Fading	SAE J 1885 225.6 KJ/m2	4/5 GS
Resistance to Heat Aging	7 days - 100°C /- 2°C	4/5GS
Soiling & Cleanability	FLTM BN 112-08 - Synthetic Soil	4/5GS
Soiling & Cleanability	FLTM BN 112-08 - Grease	5GS
Soiling & Cleanability	FLTM BN 112-08 - Orange Juice	4/5GS
Soiling & Cleanability	FLTM BN 112-08 - Coffee	4/5GS
Soiling & Cleanability	FLTM BN 112-08 - Ketchup	4/5GS
Resistance to Cleaning Agents	FLTM BN 107-01 - Window Cleaner with Ammonia	4/5GS
Resistance to Cleaning Agents	FLTM BN 107-01 - All-Purpose Cleaner	4/5GS
Resistance to Cleaning Agents	FLTM BN 107-01 - IPA 50%	4GS
Resistance to Crocking	FLTM BN 107-01 - Dry	4/5GS
Resistance to Crocking	FLTM BN 107-01 - Wet	4/5GS
Resistance to Flexing	DIN 53351 - In the cold at -10°C; 30,000 foldings	PASSED
Resistance to Flexing	DIN 53351 - Dry; 100,000 foldings	PASSED
Taber Test	ASTM D 3884 - 500 Cycles CS10 1 Kg	PASSED
Taber Test	ASTM D 3884 - 300 Cycles H18 500g	PASSED
Wet Rubbing 1000 Cycles	DIN 533 39	4/5GS
Resistance to Scuffing	SAE J365	6 GRADE
Odor	FLTM BO 131-03	2
Shrinkage	FLTM BN 105-03	3.69%
Flammability	FMVSS-302	0



LeatherShield™



Antibacterial

